

This listing of claims will replace all prior versions and listings of claims in the application:

Listing of Claims:

1. *(Currently Amended)* A method of producing a frangible fiberglass insulation batt, the method comprising
passing a stream of uncured fiberglass insulation through a cutter to cut the uncured fiberglass insulation to form side-by-side separate strips separated by a gap,
applying a binder to portions of at least one of the side-by-side separate strips along the gap, and then
passing the two side-by-side separate strips through a curing oven to expose the strips and the binder applied to portions of at least one of the side-by-side separate strips along the gap to a curing heat to polymerize the binder to establish a frangible binder bridge spanning the gap to produce a frangible cured fiberglass insulation batt.
2. *(Original)* The method of claim 1, wherein the act of applying a binder to portions of at least one of the side-by-side separate strips along the gap comprises
intercepting and deflecting the stream of fiberglass insulation exiting the cutter to separate the two side-by-side strips along a cut line therebetween to expose side edges of the strips and provide a widened gap between the strips.
3. *(Original)* The method of claim 2, wherein the act of applying a binder to portions of at least one of the side-by-side separate strips further comprises dispensing a binder onto one or both of the opposing side edges of the strips.
4. *(Original)* The method of claim 3, wherein the act of applying a binder to portions of at least one of the side-by-side separate strips further comprises manipulating at least one of the strips to arrange the opposing side edges of the strips to cause binder dispensed on one or both of the opposing side edges to polymerize during exposure to the curing heat to bond with the strips to establish the frangible polymerized binder bridge.
5. *(Original)* The method of claim 3, wherein the act of applying a binder to portions of at least one of the side-by-side separate strips further comprises mating the opposing side edges of the strips to cause any binder deposited therebetween to polymerize during exposure to the curing heat to establish the frangible polymerized binder bridge.

6. *(Original)* The method of claim 2, wherein the act of applying a binder to portions of at least one of the side-by-side separate strips further comprises dispensing a binder into the widened gap between the strips.

7. *(Original)* The method of claim 6, wherein the act of applying a binder to portions of at least one of the side-by-side separate strips further comprises mating the side-by-side separate strips to cause any binder deposited therebetween to polymerize during exposure to the curing heat to establish the frangible polymerized binder bridge.

8. *(Original)* The method of claim 1, wherein the act of applying a binder to portions of at least one of the side-by-side separate strips along the gap comprises the acts of exposing opposing side edges of the strips lying along the gap and dispensing a binder on one or both of the opposing side edges of the strips.

9. *(Original)* The method of claim 8, wherein the act of applying a binder to portions of at least one of the side-by-side separate strips along the gap further comprises manipulating at least one of the strips to arrange the opposing side edges of the strips to cause binder dispensed on one or both of the opposing side edges to polymerize during exposure to the curing heat to bond with the strips to establish the frangible polymerized binder bridge

10. *(Original)* The method of claim 8, wherein the act of applying a binder to portions of at least one of the side-by-side separate strips along the gap further comprises mating the opposing side edges of the strips to cause any binder deposited therebetween to polymerize during exposure to the curing heat to establish the frangible polymerized binder bridge.

11. *(Original)* The method of claim 1, wherein the act of applying a binder to portions of at least one of the side-by-side separate strips along the gap further comprises the acts of locating a dispenser in the gap and using the dispenser to dispense a binder into the gap between the strips.

12. *(Original)* The method of claim 11, wherein the act of applying a binder to portions of at least one of the side-by-side separate strips along the gap further comprises mating the side-by-side separate strips to cause any binder deposited therebetween to polymerize during exposure to the curing heat to establish the frangible polymerized binder bridge.

13. *(Currently Amended)* A method of producing a frangible fiberglass insulation batt, the method comprising

- passing uncured fiberglass insulation through a cutter to cut the uncured fiberglass insulation to form side-by-side separate strips separated by a gap,
- using a strip separator to move portions of the side-by-side separate strips away from one another to provide a widened gap between the strips,
- dispensing a binder into the widened gap between the strips, and
- passing the two side-by-side separate strips through a curing oven to expose the strips and binder dispensed into the widened gap between the strips to a curing heat to polymerize the binder to establish a frangible binder bridge spanning the gap to produce a frangible cured fiberglass insulated batt.

14. *(Currently Amended)* ~~The method of claim 13~~ A method of producing a frangible fiberglass insulation batt, the method comprising

- passing fiberglass insulation through a cutter to cut the fiberglass insulation to form side-by-side separate strips separated by a gap,
- using a strip separator to move portions of the side-by-side separate strips away from one another to provide a widened gap between the strips,
- dispensing a binder into the widened gap between the strips, and
- passing the two side-by-side separate strips through a curing oven to expose the strips and binder dispensed into the widened gap between the strips to a curing heat to polymerize the binder to establish a frangible binder bridge spanning the gap to produce a frangible fiberglass insulated batt, wherein the strip separator comprises a knife blade mounted for oscillatory movement in the gap and an oscillator coupled to the knife blade and configured to oscillate the knife blade in the gap to provide the widened gap between the strips.

15. *(Currently Amended)* ~~The method of claim 13~~ A method of producing a frangible fiberglass insulation batt, the method comprising
passing fiberglass insulation through a cutter to cut the fiberglass insulation to form side-by-side separate strips separated by a gap,
using a strip separator to move portions of the side-by-side separate strips away from one another to provide a widened gap between the strips,
dispensing a binder into the widened gap between the strips, and
passing the two side-by-side separate strips through a curing oven to expose the strips and binder dispensed into the widened gap between the strips to a curing heat to polymerize the binder to establish a frangible binder bridge spanning the gap to produce a frangible fiberglass insulated batt, wherein the strip separator comprises an air knife providing means for discharging pressurized air into the gap to provide the widened gap between the strips.

16. *(Currently Amended)* ~~The method of claim 13~~ A method of producing a frangible fiberglass insulation batt, the method comprising
passing fiberglass insulation through a cutter to cut the fiberglass insulation to form side-by-side separate strips separated by a gap,
using a strip separator to move portions of the side-by-side separate strips away from one another to provide a widened gap between the strips,
dispensing a binder into the widened gap between the strips, and
passing the two side-by-side separate strips through a curing oven to expose the strips and binder dispensed into the widened gap between the strips to a curing heat to polymerize the binder to establish a frangible binder bridge spanning the gap to produce a frangible fiberglass insulated batt, wherein the strip separator comprises a conduit arranged to intercept the side-by-side separate strips along the gap and formed to include means for discharging pressurized air into the gap to provide the widened gap between the strips.

17. *(Original)* The method of claim 16, wherein the conduit further includes means for dispensing binder into the widened gap to accomplish the act of dispensing a binder into the widened gap between the strips.

18. *(Currently Amended)* ~~The method of claim 13~~ A method of producing a frangible fiberglass insulation batt, the method comprising
passing fiberglass insulation through a cutter to cut the fiberglass insulation to form side-by-side separate strips separated by a gap,
using a strip separator to move portions of the side-by-side separate strips away from one another to provide a widened gap between the strips,
dispensing a binder into the widened gap between the strips, and
passing the two side-by-side separate strips through a curing oven to expose the strips and binder dispensed into the widened gap between the strips to a curing heat to polymerize the binder to establish a frangible binder bridge spanning the gap to produce a frangible fiberglass insulated batt, wherein the strip separator comprises a ram and means for moving the ram to engage the side-by-side separate strips as the strips move relative to the ram to form a series of binder-receiver pockets in the strips along the gap, which binder-receiver pockets cooperate to form the widened gap.

19. *(Original)* The method of claim 13, wherein the act of using a strip separator to move portions of the side-by-side separate strips away from one another to provide a widened gap between the strips comprises the act of applying a force to one or both of a first side edge of a first of the strips and a second side edge of a second of the strips, the first and second side edges lying in opposed relation to one another to define the gap therebetween, to provide the widened gap between the strips.

20. *(Original)* The method of claim 19, wherein the act of dispensing a binder into the widened gap between the strips comprises discharging a binder onto one or both of the first and second side edges of the strips.

21. *(Original)* The method of claim 20, wherein the act of dispensing a binder into the widened gap between the strips further comprises manipulating at least one of the strips to arrange the first and second side edges to cause binder dispensed on one or both of the first and second side edges to polymerize during exposure to curing heat to bond with the strips to establish the frangible polymerized binder bridge.

22. *(Original)* The method of claim 20, wherein the act of dispensing a binder into the widened gap between the strips further comprises mating the first and second side edges to cause only binder deposited therebetween to polymerize during exposure to curing heat to establish the frangible polymerized binder bridge.

23. *(Currently Amended)* A method of producing a frangible fiberglass insulation batt, the method comprising
providing two strips of uncured fiberglass insulation separated by a gap,
dispensing a binder into the gap to contact the two strips, and
exposing the two strips and the binder in the gap therebetween to a curing heat to polymerize the binder in the gap to establish a frangible binder bridge spanning the gap to produce a frangible cured fiberglass insulation batt.

24. *(Currently Amended)* A method of producing a frangible fiberglass insulation batt, the method comprising
cutting uncured fiberglass insulation to form side-by-side strips separated by a gap,
separating the side-by-side strips to widen the gap therebetween,
dispensing a binder into the gap to contact opposing side edges of the strips
defining the gap therebetween,
mating the opposing side edges to retain binder in the gap, and
heating the binder in the gap to establish a frangible binder bridge spanning the gap to produce a frangible cured fiberglass insulation batt.

25. *(New)* A method of producing a frangible fiberglass insulation batt, the method comprising

cutting uncured fiberglass insulation to form side-by-side first and second strips separated by a first gap and a third strip separated from the second strip by a second gap,

dispensing a binder into the first gap to contact opposing side edges of the first and second strips defining the first gap therebetween,

dispensing a binder into the second gap to contact opposing side edges of the second and third strips defining the second gap therebetween,

mating the opposing side edges of the first and second strips to retain binder in the first gap and the opposite side edges of the second and third strips to retain binder in the second gap, and

heating the binder in the first and second gaps to establish a first binder bridge spanning the first gap and a second binder bridge spanning the second gap to produce a frangible cured fiberglass insulation batt.